

IS: 12269



CM/L - 2023022

# ACC

Doc.no.: WD/LAB/FM/08

## Wadi Cement Work Ordinary Portland Cement 53 grade

Week No. 38 (16.09.2016 to 22.09.2016)

Sl.no.	Characteristics	Unit	Actual	IS 12269 :2013 specified requirement
1	<b>Chemical characteristics</b>			
	Magnesia (MgO)	%	0.8	Max. 6.0
	Sulphuric anhydride (SO <sub>3</sub> )	%	2.8	Max. 3.5
	Chloride (Cl <sup>-</sup> )	%	0.021	1. Max. 0.1 for structures other than prestressed concrete 2. Max. 0.05 for Prestressed concrete structures
	Insoluble Residue (IR)	%	0.6	Max. 4.0
	Loss on Ignition	%	1.8	Max. 4.0
	Lime Saturation Factor (LSF)		0.90	0.80 to 1.02
	Tri Calcium Aluminate (C <sub>3</sub> A)	%	6.74	-
2	<b>Physical characteristics</b>			
	Fineness (by Blaine method)	m <sup>2</sup> /kg	311	Min. 225
	<b>Soundness</b>			
	(a) Le chatelier method	mm	1.5	Max. 10
	(b) Autoclave test method	%	0.07	Max. 0.8
	<b>Setting time</b>			
	(a) Initial Setting Time (IST)	Minutes	135	Min. 30
	(b) Final Setting Time (FST)	Minutes	195	Max. 600
	<b>Compressive Strength</b>			
	(a) 3-days	MPa	37.4	27
	(b) 7-days	MPa	46.9	37
	(c) 28-days	MPa	Awaited	53
	Normal consistency	%	27.8	-
	Temperature during Testing	°C	27+/-2	-

  
 Head Quality Assurance