





WORK TEST CERTIFICATE

53 Grade Ordinary Portland Cement

Despatched during Week No.		41	From	From 08/10/18		То	14/10/18		
Test Certificate No.		41	Referenc	. No		WCV	N/IMS/QA/FM/08		
Dated		12/11/18 Reference		e INO.		WCW/IIWS/QA/FIW/06			
S.N.	Pa	arameters		Results Obtained	Requirement as per IS 269 : 2015 (Variety: OPC 53)				
	Chemical Composition								
1	Lime Saturation Factor (CaO – 0.7 *SO ₃) / (2.8* SiO ₂ + 1.2* Al ₂ O ₃ + 0.65* Fe ₂ O ₃)			0.88	Not greater than 1.02 and not less than 0.80				
	Ratio of % Alumina to that of Iron Oxide Al ₂ O ₃ / Fe ₂ O ₃			1.28	Not less than 0.66				
	Insoluble Residue (% by mass)			0.60	Not more than 5.0 %				
	Magnesia (% by mass)			0.95	Not more than 6.0 %				
	Sulphuric Anhydride (% by mass)			2.93	Not More than 3.5 %				
	Total loss on Ignition (%)			1.70	Not More than 4.0 %				
	Chloride Content (%)			0.010	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures				
	Physical Analysis			•	•				
2	Fineness								
2	Blaine's Specific Surface	ce Area (m² / kg)		313	Not Less th	nan 225			
3	Compressive Strength (MPa)								
	72 ± 1h (3 Days)			36.4	Not less than 27.0				
3	168 ± 2h (7 Days)			46.2	Not less than 37.0				
	672 ± 4h (28 Days) *			58.5	Not less than 53.0				
4	Setting Time (Minutes)							
	Initial	Initial			Not less than 30				
	Final	Final			Not more than 600				
5	Soundness								
	Le-Chatelier Expansion (mm)			1.00	Not more than 10.0				
	Auto-Clave Expansion (%)			0.060	Not more than 0.8				
6	Normal Consistency (%)			27.50					
	Temp. During Testing (ouring Testing (⁰ C)			(27 ± 2) ⁰ C				

The above cement complies with the requirements of IS 269 : 2015 (Variety: OPC 53) for 53 Grade Ordinary Portland Cement

Manager (QA)