



LICENCE NO . CM/L-8099186



WEEK No 26

DATE OF ISSUE 08.07.2016

CHEMICAL / PHYSICAL REQUIREMENTS	SPECIFICATION CLAUSE No.	REQUIREMENT AS PER IS No.12269 – 2013 AMENDMENT No. 6	RESULTS OBTAINED
 CHEMICAL REQUIREMENTS : # (i) Ratio of Percentage of Lime to # percentage of silica, alumina and iron oxide CaO - 0.7SO₃ 	5 5.1	Not Greater than 1.02 And not less than 0.80	0.924
2.8 SiO ₂ + 1.2 Al ₂ O ₃ + 0.65 Fe ₂ O ₃			
(ii) Ratio of percentage of alumina to that # of iron oxide	5.1	Not less than 0.66	1.56
(iii) Insoluble residue, percent by mass #	5.1	Not more than 4.0	2.72
(iv) Magnesia, percent by mass #	5.1	Not more than 6.0	2.38
 (v) Total sulphur calculated as Sulphuric # Anhydride (SO₃), Percent by mass 	5.1	Not more than 3.5	2.24
(vi) Total loss on ignition #	5.1	Not more than 4%	2.20
(vii) Chloride, percent by mass #	5.1	Not more than 0.1	0.044
PHYSICAL REQUIREMENTS :	6		
(i) FINENESS : SP. SURFACE	6.1	Not less than 225 m2/kg	360
(ii) SOUNDNESS : a) Le-chatelier method Expansion	6.2	Not more than 10 mm	1.00
b) Auto clave test expansion C.NO.T-0720		Not more than 0.8%	0.050
(iii) SETTING TIMEa) Initial Setting time in Minutes	6.3	Not less than 30	115
b) Final setting time in Minutes		Not more than 600	150
(iv) COMPRESIVE STRENGTH 72 ± 1 Hours (3 Days)	6.4	Not less than 27 MPa	43.0
168 ± 2 Hours (7 Days)		Not less than 37 MPa	51.0
672 ± 4 Hours (28 Days)		Not less than 53 MPa	Under Testing

REMARKS : The test results complies with the requirements of IS: 12269–2013for 53 grade OPC for All Chemical requirements and Physical requirements including Compressive Strength up to 7- day. Test Protocol : IS:4032 and IS:4031. # Not covered under NABL Accreditation at present

Note : Results reported above are the average test results of all samples testing during relevant week.

CERTIFIED ISO 9001:2008 ISO 14001:2004

OHSAS 18001:2007

eee

HOD(QC)