

SANGHI INDUSTRIES LIMITED QUALITY CONTROL LABORATORY

Sanghipuram - 370 511.

Turning Dreams into Concrete Reality Tal.: Abdasa, Dist.: Kutch, State: Gujarat

(NABL ACCREDITED LABORATORY) CM/L 7431062

T - 1233, T - 1234 Phone (02831) 274131, 274132, 274135, Fax: (02831) 274106,274115, e-mail: info@sanghicement.com

Page No. 1/1

Certificate No. CMD/OPC/20/11/15

: 21.11.2015 **Lot Create Date**

Material : CEMENT OPC53GR

Lab Code 324/CM/20 Sample Received From Packing Plant **Address SIL-Sanghipuram**

Reference : Day Average Com Despatch **During of testing Period** : 21.11.2015 To 19.12.2015

: IS 4031 & IS 4032 Tested as per

Date of Sample : 20.11.2015

Month 11 Week 47

NABL/TP/F30

Issue No.6, Amnd.No.: 01, Eff. Dt.: 29.09.2015

RESULTS

OBTAINED

2.24

1.25

2.65

2.57

0.059

0.91

1.32

7.49

323

30.0

115

195

1.00

0.08

23.0

43.0

55.5

68.0

TEST CERTIFICATE **PARAMETERS TESTED** REQUIREMENTS AS PER IS 12269 : 2013 1. Chemical Testing **LESS THAN 4.00%** Loss on Ignition **LESS THAN 4.00%** Insoluble Residue **LESS THAN 3.50%** SO3 **LESS THAN 6.00%** MgO **LESS THAN 0.10%** Chlolride 0.80% To 1.02% LSF **MORE THAN 0.66%** ΑM C3A 2. Mechanical Testing MORE THAN 225.00m2/kg **Specific Surface Normal Consistency** MORE THAN 30.00min **Setting Time - Initial** LESS THAN 600.00min **Setting Time - Final LESS THAN 10.00MM** Soundness Lechatelier **LESS THAN 0.80% Soundness Autoclave** MORE THAN 20.00MPa Comp. Strength - 24 Hrs. * **MORE THAN 27.00MPa** Comp. Strength - 72 ± 1 Hrs.

Conditions:

S

A N G

H

C

É M

Ε

N

T

S

A N

G

Н

C

E M

E N

- 1. The test results pertain to the sample received only.
- 2. This report is being issued with a specific understanding that SIL QC LAB will not in any way be involved in action following the interpretation of above results.

MORE THAN 37.00MPa

MORE THAN 53.00MPa

- 3. This report shall not be re-produced except in full without written approval from SIL QC LAB.
- 1 Day testing is out of NABL scope.

Comp. Strength - 168 ± 2 Hrs

Comp. Strength - 672 ± 4 Hrs.

Authorised Signatory

Quality Manager

S Α Ν G Н C Ē M Ε N Т S N G н C Ε M Е